

GOLD BALL

Woodfree offset printing paper (92 ISO Brightness/140CIE Whiteness) Good paper profile on both sides, suitable for double sided printing Good smoothness and printability.


FEATURES & BENEFITS

- For forms and general offset printing applications
- Paper Offset (92 ISO Brightness/140CIE Whiteness)


END USE APPLICATION



Books



Writing Paper



Manuals

Property	Unit	Test Method Reference	Basis Weight (LOW GRAMMAGE)												
Basis Weight	g/m ² (±4)	ISO 536	56	60	70	75	80	90	95	100	105	110	120	140	150
Thickness	µm (±4)	ISO 534	74	78	92	97	102	110	115	122	127	130	142	165	175
Smoothness	s (±10)	ISO 5627	35	35	35	35	30	30	30	30	30	30	30	25	25
Humidity	%(±1.5)	ISO 287	6	6	6	6	6	6	6	6	6	6	6	6	6
Brightness	%(±1.5)	ISO 2470	92	92	92	92	92	92	92	92	92	92	92	92	92
Opacity	%(±3)	ISO 2471	86	88	92	93	94	95	95	96	96	97	98	98	98
Wax Pick	A (±2)	T459	16	16	16	16	16	16	16	16	16	16	16	14	14

Property	Unit	Test Method Reference	Basis Weight (HIGH GRAMMAGE)												
Basis Weight	g/m ² (±4)	ISO 536	170	180	185	190	200	210	220	230	240	250	270	300	350
Thickness	µm (±4)	ISO 534	200	220	225	230	240	250	263	275	288	300	325	360	405
Smoothness	s (±10)	ISO 5627	25	25	25	25	25	20	20	20	20	20	20	20	20
Humidity	%(±1.5)	ISO 287	6	6	6	6	6	6	6	6	6	6	6	6	6
Brightness	%(±1.5)	ISO 2470	92	92	92	92	92	92	92	92	92	92	92	92	92
Opacity	%(±3)	ISO 2471	98	98	98	98	98	98	98	98	98	98	98	98	98
Wax Pick	A (±2)	T459	14	14	14	14	14	14	14	14	14	14	14	14	14

